



Tridol^{C6} ATF 3-6 LT

Alcohol Resistant Aqueous
Film-Forming Foam (AR-AFFF)
Concentrate


Integrity

*Doing what's right, rather than
what's convenient*

Angus Fire prides itself on the open and honest way in which we conduct our business throughout the world. Our foams are an extension of our ethical beliefs and we pride ourselves in being the responsible foam manufacturer, balancing high performance with minimal environmental impact. Our C6 foams contain no PFOA and no PFOS, in accordance with US EPA Stewardship Programme 2010/15 and EU Directive 2006/122/EC and amended Council Directive 76/769/EEC.

C6 Fluorosurfactants

These are the most effective agents currently available to tackle serious flammable liquid fires, providing firefighter safety and asset protection. Angus foams containing C6 surfactants utilise the very latest in firefighting foam technologies, developed and refined specifically to lower the environmental impact without reducing performance.



- Highly versatile
- Film-forming on hydrocarbons for fast flame knockdown and extinguishment
- Superior burnback resistance and post-fire security

Tridol^{C6} ATF 3-6 LT is a cost-effective Alcohol Resistant Aqueous Film-Forming Foam (AR-AFFF) concentrate for extinguishing and securing flammable hydrocarbon and polar solvent liquid fires.

Tridol^{C6} ATF 3-6 LT is a unique combination of hydrocarbon and fluorocarbon surface active agents. It produces a vapour-sealing aqueous film that spreads rapidly over hydrocarbon surfaces to provide rapid control and extinguishment. On polar solvents an insoluble polymer membrane is formed which protects the foam blanket from the solvent.

- Highly versatile and so eliminates the need to stock a variety of foam types.
- Film-forming on hydrocarbons for fast flame knockdown and extinguishment.
- Burnback resistance and post-fire security.
- Foam blanket re-seals when ruptured by personnel or equipment.

Applications

Tridol^{C6} ATF 3-6 LT is used in high risk situations where hydrocarbons (such as crude oil, gasoline, diesel fuel, aviation kerosene) and/or polar solvents (such as alcohols, ketones, esters, and ethers) are stored, processed, or transported.

Approvals and Listings

Tridol^{C6} ATF 3-6 LT is independently tested and certified to EN1568:2008 Parts 3 & 4.

Equipment

Tridol^{C6} ATF 3-6 LT is intended for use at 3% (3 parts concentrate to 97 parts of water) on hydrocarbons and 6% on polar solvents.

Tridol^{C6} ATF 3-6 LT is readily proportioned using conventional foam proportioning equipment such as portable and fixed foam proportioners at temperatures as low as -15°C (5°F).

Tridol^{C6} ATF 3-6 LT can be used with air aspirating discharge devices such as low expansion branchpipes, monitors, top pourer sets, rimseal foam pourers, foam/water sprinklers, and base (sub-surface) injection systems at temperatures as low as -15°C (5°F).

Tridol^{C6} ATF 3-6 LT can be used with non-aspirating discharge devices such as spray/fog branchpipes and nozzles, monitors, and spray/fog sprinklers. Non-aspirated application is not recommended as the primary method of attack for major fires where a stable foam cover is essential.

Tridol[®] ATF 3-6 LT

Alcohol Resistant Aqueous Film-Forming Foam (AR-AFFF) Concentrate

Compatibility

Tridol[®] ATF 3-6 LT is suitable for use in combination with:

- Soft or hard, fresh, brackish or sea water.
- Dry powder extinguishing agents either separately or as twin agent systems.
- Expanded protein-based or synthetic foams for application to a fire in sequence or simultaneously.

Environment

Tridol[®] ATF 3-6 LT demonstrates low toxicity to aquatic organisms.

Storage

Tridol[®] ATF 3-6 LT is exceptionally stable in long-term storage. A shelf-life of at least ten years can be expected if it is stored properly.

Disposal

For fire water runoff and accidental

spillage please refer to Angus Fire's Foam Disposal Guide and MSDS for more information.

Reliability

Tridol[®] ATF 3-6 LT is produced to rigorous quality control standards to ensure consistent fire performance and excellent product reliability.

Angus Fire operates a quality management system which complies with the requirements of BS EN ISO 9001.

Typical Physico-Chemical Properties

Appearance		Light Yellow Liquid
Specific gravity @ 20°C (68°F)		1.02 - 1.06
pH @ 20°C (68°F)		7.0 - 8.0
Non-Newtonian fluid that is pseudoplastic (shear thinning)		
Viscosity @ 20°C (68°F) using No.4 spindle at 60 rpm	cP	900 - 2100
Maximum continuous storage temperature	°C (°F)	49 (120)
Maximum intermittent storage temperature	°C (°F)	60 (140)
Freezing point	°C (°F)	-16 (3.2)
Effect of freeze/thaw		No loss of performance
UL Lowest use temperature	°C (°F)	-6.7 (20)

Typical Foam Properties

Foam generated using the U.K. Defence Standard DEF42-40 5 lpm branchpipe at 7 Bar pressure. Foam collected in a 1630 ml N.F.P.A. drainage pan.

Induction rate		3	6
Expansion ratio		≥ 7:1	≥ 8:1
25% drainage time	min/sec	≥ 8'00"	≥ 15'00"

Packing Specification

	Plastic Square	Plastic Square	Plastic Cylindrical	Plastic Cylindrical	Ecobulk MX
Capacity	25 litres	5 US gallons	200 litres	55 US gallons	1000 litres
Empty weight (kg)	1.2	0.8	9.0	9.0	70
Filled weight (kg)	27	21	217	226	1110
Dimensions (mm)	448 x 286 x 286	402 x 293 x 240	580 D x 922 H	580 D x 922 H	1200 L x 1000 W x 1160 H
Part number	FN0334G0P	FN0334T0P	FN0334J0P	FN0334W0P	FN0334L8



EMERGENCY FOAM SERVICE Call +44 (0) 15242 61166 – 24 hours a day, every day

INTERNATIONAL SALES

Angus Fire Ltd

Angus House, Haddenham Business Park,
Pegasus Way, Haddenham, Aylesbury, HP17 8LB, UK
Tel: +44 (0)1844 293600 • Fax: +44 (0)1844 293664

UK SALES

Angus Fire Ltd

Station Road, Bentham, Lancaster, LA2 7NA, UK
Tel: +44 (0)1524 264000 • Fax: +44 (0)1524 261580

Angus Fire operates a continuous programme of product development. The right is therefore reserved to modify any specification without prior notice and Angus Fire should be contacted to ensure that the current issues of all technical data sheets are used.

© Angus Fire 5272C6/6 09.17
Tridol[®] is a registered trademark of the Angus International group.